

ItalSens Gold SPE IS-W1-3.C1.RS.35

1 Description



Figure 1 ItalSens IS-W1-3.C1.RS.35 cut into single units

The three-electrode electrochemical cell has a gold working electrode, suitable for a wide range of analytical applications. Each electrode is produced by screen-printing technology and constitutes a circular gold working electrode (3 mm diameter), a silver pseudo reference electrode, and a gold counter electrode. The small electrode dimensions reduce the required sample volumes, and the low costs permit disposable use.

The electrodes are delivered in sheets comprising 30 pieces, which are already cut for you.

Samples can be applied as a droplet due to the design of the electrodes. This avoids the waste of reagents and samples. The electrodes can be modified through direct adsorption, chemical binding, etc., and a wide range of biomolecules can be linked to the electrode surface. These customizations make the gold electrodes suitable for a broad spectrum of applications.

1.1 Application Advice

The silver pseudo-reference electrode shows higher stability in the presence of chloride ions. Hence, it is recommended that measurements are carried out in solutions with a chloride ion concentration of at least 10 mM.

We also recommend electropolishing the electrodes before using them, especially for self-assembled monolayer formation. Electropolishing can be easily performed by cyclic voltammetry. Put 100 μ L of 0.5 M sulfuric acid on the three electrodes or immerse the three electrodes in 0.5 M sulfuric acid. Cyclic Voltammetry with 30 Scans from -0.7 to 1.6 V with a scan rate of 0.3 V/s should suffice.

2 Technical Specifications

Dimensions: 1 x 3.5 cm

Working electrode dimensions: 7.07 mm²

Substrate: Valox

Thickness: 650 μ m

Contact pad pitch: 2.54 mm

Coefficient of Variation (CV, After polishing) (n = 20): 9 %

3 Measurements

3.1 Electropolishing

All measurements were performed with a droplet of solution covering all three electrodes of the cell. The solution contained 0.5 M H_2SO_4 (see chapter 1.1).




Figure 2 CV, IS-W1-3.C1.RS.35, scan rate 0.1 V/s, E step 5 mV, 1st, 5th, 10th, 15th, 20th, 25th, and 30th scan

3.2 Cyclic Voltammogram

All measurements were performed with a droplet of solution covering all three electrodes of the cell. The solution contained 2.5 mM $\text{K}_3[\text{Fe}(\text{CN})_6]$, 2.5 mM $\text{K}_4[\text{Fe}(\text{CN})_6]$, and 0.1 M KCl.




Figure 3 CV, unpolished IS-W1-3.C1.RS.35, scan rate 0.1 V/s, E step 5 mV, 1st (blue), 2nd (red), and 3rd (green) scan




Figure 4 CV, electropolished IS-W1-3.C1.RS.35, scan rate 0.1 V/s, E step 5 mV, 1st (blue), 2nd (red), and 3rd (green) scan

3.3 Electrochemical Impedance Spectroscopy




Figure 5 EIS, three unpolished IS-W1-3.C1.RS.35, E dc OCP, E ac 10 mV, frequency range 0.1 Hz to 1 MHz

After electropolishing the IS-W1-3.C1.RS.35 show usually lower impedance and a lower variation during EIS.




Figure 6 EIS, three polished IS-W1-3.C1.RS.35, E_{dc} OCP, E_{ac} 10 mV, frequency range 0.1 Hz to 1 MHz

4 Application Examples from Peer-Reviewed Publications

- F. Lucarelli, G. Marrazza, M. Mascini, "Enzyme-based impedimetric detection of PCR products using oligonucleotide modified screen-printed gold electrodes", *Biosensors and Bioelectronics*, 20, 10, 2005, 2001-2009. <https://doi.org/10.1016/j.bios.2004.08.025>
- S. Laschi, I. Palchetti, M. Mascini, "Gold-based screen-printed sensor for detection of trace lead", *Sensors and Actuators B: Chemical*, 114, 1, 2006, 460-465. <https://doi.org/10.1016/j.snb.2005.05.028>
- S. Laschi, G. Bagni, I. Palchetti, M. Mascini, "As(III) voltammetric detection by means of disposable screen-printed gold electrochemical sensors", *Analytical Letters*, 40, 16, 3002 - 3013. <https://doi.org/10.1080/00032710701645703>